

Certificate of Conformity Summary



Purfleet - July 2022

Combinations of Regen GGBS supplied from Hanson Cement in combination with the CEM I Portland Cements and CEM II Portland Limestone Cements (PLC) listed below conform with the requirements of BS 8500-2:2015 over the indicated range of proportions. The compressive strength results are for tests carried out in accordance with BS EN 197-1 with 50% Regen GGBS in combination with the indicated CEM I Portland Cement and 20% Regen GGBS in combination with the indicated CEM II Portland Limestone Cements (PLC)

Portland Cement Source	Compressive Strength N/mm2		Regen GGBS Percentage Range					
			42.5L		32.5L		22.5	
	7 day	28 day	Min	Max	Min	Max	Min	Max
ALHANDRA 52.5R	29.2	52.6	30	63	52	78	71	80
PADESWOOD PLC	41.6	56.3	1	30	n/a	n/a	n/a	n/a
ABERTHAW	31.4	51.3	22	70	53	80	77	80
KETTON	30.1	50.7	6	61	47	76	70	80
MACEIRA-LIZ	28.8	53.5	6	71	59	80	77	80
CAULDON 52.5N	29.8	49.4	6	66	49	80	74	80
PADESWOOD	33.8	51.6	6	67	46	80	75	80
TUNSTEAD	28.9	52.0	18	63	54	77	70	80
RIBBLESDALE	32.7	51.1	24	73	51	80	79	80
RUGBY	31.0	51.5	6	65	54	78	72	80
LEMONA	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
CHATHAM LAGERDORF	35.7	56.1	6	64	57	76	70	80
PLATIN	29.5	53.1	6	65	47	80	74	80
TILBURY	31.2	50.8	26	65	52	80	73	80
QUINN	32.9	53.5	n/a	n/a	n/a	n/a	n/a	n/a
HOPE	30.0	50.2	6	63	51	79	72	80
LIMERICK	28.5	50.8	6	59	51	74	66	80
METAPORQUERA	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
KETTON PLC	38.2	56.5	1	30	n/a	n/a	n/a	n/a
ABONO	31.9	53.0	6	63	55	78	71	80
GHENT	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
HOPE PLC	40.4	54.2	1	30	n/a	n/a	n/a	n/a
SEVILLE	31.0	51.3	6	63	51	80	73	80
		Ì						

Combination Designation	Percentage Regen GGBS			
(Table 1 BS 8500-2)	Not Less Than	Not More Than		
CIIA (With CEM I)	6	20		
CIIA (With PLC)	Depends on limestone content in cement			
CIIB-M	Depends on limestone content in cement			
CIIB-S	21	35		
CIIIA	36	65		
CIIIB	66	80		

The Regen GGBS contained no additional materials others than those permitted according to BS EN 15167-1.

Hanson Cement has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Hanson Cement for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.

Signed:

1 Cerdial

Dr Nina Cardinal, Dipl.Ing., CEng, MiMMM National Technical Manager

UK

1333-CPR-00133