

Certificate of Conformity Summary



Teesside SF - June 2023

Combinations of Regen GGBS supplied from Hanson Cement in combination with the CEM I Portland Cements and CEM II Portland Limestone Cements (PLC) listed below conform with the requirements of BS 8500-2:2015 over the indicated range of proportions. The compressive strength results are for tests carried out in accordance with BS EN 197-1 with 50% Regen GGBS in combination with the indicated CEM I Portland Cement and 20% Regen GGBS in combination with the indicated CEM II Portland Limestone Cements (PLC) The combination of cement sources in bold text have been evaluated for conformity for less than six months.

Portland Cement Source	Compressive Strength N/mm2		Regen GGBS Percentage Range					
			42.5L		32.5L		22.5	
	7 day	28 day	Min	Max	Min	Max	Min	Max
KETTON	32.3	49.8	6	66	52	77	73	80
CAULDON 52.5N	31.9	51.1	6	61	53	72	67	80
PADESWOOD	32.2	49.5	6	66	52	77	72	80
TUNSTEAD	31.6	54.0	18	62	54	74	68	80
RIBBLESDALE	33.9	53.3	20	67	55	77	72	80
RUGBY	34.1	52.0	6	63	54	75	70	80
GLASGOW LAGERDORF	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
DUNBAR	26.6	50.2	32	67	49	80	76	80
PLATIN	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
COOKSTOWN	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
ALHANDRA 52.5R	33.6	53.9	36	69	58	80	75	80
HOPE	31.5	51.0	6	63	54	74	69	80
ALCANAR	31.2	52.8	35	68	58	78	74	80
LAGAN	33.2	54.2	6	70	58	80	77	80
OUTAO	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
RIBBLESDALE PLC	43.0	56.2	1	30	n/a	n/a	n/a	n/a
PADESWOOD PLC	41.3	56.0	12	30	n/a	n/a	n/a	n/a
HOPE PLC	40.5	54.5	1	30	n/a	n/a	n/a	n/a
OGGAZ	34.2	53.9	37	71	64	79	75	80

Combination Designation	Percentage Regen GGBS			
(Table 1 BS 8500-2)	Not Less Than	Not More Than		
CIIA (With CEM I)	6	20		
CIIA (With PLC)	Depends on limestone content in cement			
CIIB-M	Depends on limestone content in cement			
CIIB-S	21	35		
CIIIA	36	65		
CIIIB	66	80		

The Regen GGBS contained no additional materials others than those permitted according to BS EN 15167-1.

Hanson Cement has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Hanson Cement for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.

Signed:

10 Cerdial

Dr Nina Cardinal, Dipl.Ing., CEng, MiMMM National Technical Manager

UK

1333-CPR-00212