

## **Conformity Certificate**



## Regen Ground Granulated Blastfurnace Slag Produced at Sample Period

## Purfleet January 2024

## **Certificate of Conformity of Regen GGBS**

Spot samples of Regen GGBS were taken and tested to determine conformity to the autocontrol requirements of EN 15167-1 "Ground granulated blastfurnace slag for use in concrete, mortar and grout" following the methods given in that standard. The values reported are mean values for the monthly production period.

		Result	EN Limit
Regen GGBS Only			
Fineness m <sup>2</sup> /kg		474	min. 275
Magnesia MgO %		6	max. 18
Sulfate SO <sup>3</sup> %		0.18	max. 2.5
Sulfide S <sup>2-</sup> %		0.76	max. 2.0
Chloride Content CI %		0.01	max. 0.1
Moisture Content %		0.11	max. 1.0
Aluminia Al <sub>2</sub> O <sub>3</sub> %		14	
Note: If the value is $\ge$ 14% the '+SR' restriction will be exceeded if the C <sub>3</sub>	A of the CEM I is > 10%	6.	
Alkalis as Na2O equ. (acid so	luble)		
Certified Average Alkali (Last 25) %		≤ 1.0	
Mean Alkali content (Last 25) %		0.59	
Declared Mean : Mean last 25 + (SD last 25 x 1.64) %		0.69	
Combination of 50% Laboratory Stock CEM I Portland	Cement and 50% Rege	en GGBS	
Initial Setting Time min.		204	> 2 x PC
Activity Index %	7 days	66	min. 45
	28 days	84	min. 70
Laboratory Stock CEM I Portland Co	ement Only		
The laboratory stock CEM I Portland cement used in these	e tests was supplied by	Hanson.	
Initial Setting Time min		133	
Compressive Strength N/mm <sup>2</sup>	7 days	47.1	
	28 days	59.6	
The Regen GGBS contained no additional materials other than those demonstrate the conformity of the material sold during the montation nerver of the material sold during the montation nerver of the instruction defined to the montation nerver of the solution of the materials UK for any loss, damage, cost or expenses or otherwise.	th to the requirements c	of EN 15167	'-1.
Signed:			
b. Cerdial			UK CA
Dr Nina Cardinal, Dipl.Ing., CEng, MICT National Technical Manager		1333	3-CPR-00133