



Heidelberg Materials UK
 Second Floor, Arena Court, Crown Lane
 Maidenhead, Berkshire, SL6 8QZ
 Padeswood Works
 1333-CPR-00255



Cement Test Report

Heidelberg Materials UK
 Ketton
 Stamford
 PE9 3SX
 Tel: 0330 123 2074
 Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of
 Padeswood PLC 52,5N, BS EN 197-1:2011 - CEM II/A-LL 52,5N

Dispatched from Padeswood during week ending 10-Mar-24 (Week No. 2024-10)
 and during week ending 18-Feb-24 (Week No. 2024-7) for 28 day results

Date	Fineness Specific Surface (m ² /kg)	Setting Time Initial (mins)	Soundness Expansion (mm)	Compressive Strength			Chloride %	Alkali	
				40mm x 40mm x 160mm Mortar prisms				Certified Average Alkali % Na ₂ O eq	Standard Deviation
				2 Days (N/mm ²)	7 Days (N/mm ²)	28 Days (N/mm ²)			
05-Mar-24	530	180	1	31.5	49.0		0.04	0.58	0.04
08-Mar-24	555	190		32.5	51.5		0.04	0.58	0.04
Average	545	185	1	32.0	50.5		0.04		0.04
13-Feb-24	555	170	1	30.0	45.5	53.0	0.03	0.57	0.03
16-Feb-24	570	170		30.0	45.5	53.5	0.03	0.57	0.04
Average	565	170	1	30.0	45.5	53.5	0.03		0.03

Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Chloride content (%) = 0.07 (Max)

For and on behalf of
 HEIDELBERG MATERIALS UK

Dr Nina Cardinal, Dipl.Ing., CEng, MICT
 National Technical Manager
 Heidelberg Materials UK

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.