

Conformity Certificate



Regen Ground Granulated Blastfurnace Slag Produced at Sample Period

Port Talbot February 2024

Certificate of Conformity of Regen GGBS

Spot samples of Regen GGBS were taken and tested to determine conformity to the autocontrol requirements of EN 15167-1 "Ground granulated blastfurnace slag for use in concrete, mortar and grout" following the methods given in that standard. The values reported are mean values for the monthly production period.

		Result	EN Limit
Regen GGBS Only			
Fineness m ² /kg		441	min. 275
Magnesia MgO %		8	max. 18
Sulfate SO ³ %		0.13	max. 2.5
Sulfide S ²⁻ %		1.24	max. 2.0
Chloride Content CI %		0.00	max. 0.1
Moisture Content %		0.08	max. 1.0
Aluminia Al ₂ O ₃ %		13	
Note: If the value is \ge 14% the '+SR' restriction will be exceeded if the C ₃ A of the content of the conten	ne CEM I is > 10°	%.	
Alkalis as Na2O equ. (acid soluble)			
Certified Average Alkali (Last 25) %		≤ 1.0	
Mean Alkali content (Last 25) %		0.76	
Declared Mean: Mean last 25 + (SD last 25 x 1.64) %		0.81	
Combination of 50% Laboratory Stock CEM I Portland Cemer	nt and 50% Reg	en GGBS	
Initial Setting Time min.		220	> 2 x PC
Activity Index %	7 days	64	min. 45
	28 days	89	min. 70
Laboratory Stock CEM I Portland Cement	Only		
The laboratory stock CEM I Portland cement used in these tests	was supplied by	Hanson.	
Initial Setting Time min		130	
Compressive Strength N/mm ²	7 days	46.2	
	28 days	58.6	
The Regen GGBS contained no additional materials other than those permitt demonstrate the conformity of the material sold during the month to the receiving materials of this used an reasonable care to ensure the information never contained.			

liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence

Signed:

10 ardial

Dr Nina Cardinal, Dipl.Ing., CEng, MICT National Technical Manager

1333-CPR-00134