

Conformity Certificate



Regen Ground Granulated Blastfurnace Slag Produced at Sample Period

Port Talbot May 2024

Certificate of Conformity of Regen GGBS

Spot samples of Regen GGBS were taken and tested to determine conformity to the autocontrol requirements of EN 15167-1 "Ground granulated blastfurnace slag for use in concrete, mortar and grout" following the methods given in that standard. The values reported are mean values for the monthly production period.

			Result	EN Limit
Regen GGBS Only				
Fineness m ² /kg			403	min. 275
Magnesia MgO %			8	max. 18
Sulfate SO ³ %			0.28	max. 2.5
Sulfide S ²⁻ %			1.13	max. 2.0
Chloride Content Cl %			0.00	max. 0.1
Moisture Content %			0.13	max. 1.0
Aluminia Al₂O₃ %			13	
Note: If the value is ≥ 14% the '+SR' restriction will be exceeded if the C	S_3 A of the CEM I is >	10%		
Alkalis as Na2O equ. (acid so	oluble)			
Certified Average Alkali (Last 25) %			≤ 1.0	
Mean Alkali content (Last 25) %			0.70	
Declared Mean: Mean last 25 + (SD last 25 x 1.64) %			0.74	
Combination of 50% Laboratory Stock CEM I Portland	Cement and 50% I	Reger	n GGBS	
Initial Setting Time min.			224	> 2 x PC
Activity Index %	7 day	'S	67	min. 45
	28 da	ys	91	min. 70
Laboratory Stock CEM I Portland C	Cement Only			
The laboratory stock CEM I Portland cement used in thes	e tests was supplied	d by H	lanson.	
Initial Setting Time min			130	
Compressive Strength N/mm ²	7 day	'S	44.1	
	28 da	ys	55.4	
The Regen GGBS contained no additional materials other than those demonstrate the conformity of the material sold during the mor	•			

demonstrate the conformity of the material sold during the month to the requirements of EN 15167-1.

Tredenority waterials of the material sold during the month to the requirements of EN 15167-1.

Itability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence

Signed:

10 Cerdial

1333-CPR-00134

Dr Nina Cardinal, Dipl.Ing., CEng, MICT National Technical Manager