

## **Conformity Certificate**



## Regen Ground Granulated Blastfurnace Slag Produced at Sample Period

## Teesside May 2024

## Certificate of Conformity of Regen GGBS

Spot samples of Regen GGBS were taken and tested to determine conformity to the autocontrol requirements of EN 15167-1 "Ground granulated blastfurnace slag for use in concrete, mortar and grout" following the methods given in that standard. The values reported are mean values for the monthly production period.

		Result	EN Limit
Regen GGBS Only			
Fineness m²/kg		480	min. 275
Magnesia MgO %		6	max. 18
Sulfate SO <sup>3</sup> %		0.23	max. 2.5
Sulfide S <sup>2-</sup> %		0.60	max. 2.0
Chloride Content Cl %		0.01	max. 0.1
Moisture Content %		0.08	max. 1.0
Aluminia Al <sub>2</sub> O <sub>3</sub> %		15	
Note: If the value is $\ge$ 14% the '+SR' restriction will be exceeded if the C	$C_3A$ of the CEM I is > 10°	%.	
Alkalis as Na2O equ. (acid se	oluble)		
Certified Average Alkali (Last 25) %		≤ 1.0	
Mean Alkali content (Last 25) %		0.40	
Declared Mean : Mean last 25 + (SD last 25 x 1.64) %		0.45	
Combination of 50% Laboratory Stock CEM I Portland	I Cement and 50% Reg	en GGBS	
Initial Setting Time min.		253	> 2 x PC
Activity Index %	7 days	76	min. 45
	28 days	97	min. 70
Laboratory Stock CEM I Portland (	Cement Only		-
The laboratory stock CEM I Portland cement used in the	se tests was supplied by	Hanson.	
Initial Setting Time min		130	
Compressive Strength N/mm <sup>2</sup>	7 days	44.1	
	28 days	55.4	
The Regen GGBS contained no additional materials other than those demonstrate the conformity of the material sold during the mor			
liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expen			
Signed:			UK
U Cerdial			ČÀ
Dr Nina Cardinal, Dipl.Ing., CEng, MICT National Technical Manager		1333	3-CPR-00212