

Teesside SF - June 2024

Combinations of Regen GGBS supplied from Heidelberg Materials UK in combination with the CEM I Portland Cements and CEM II Portland Limestone Cements (PLC) listed below conform with the requirements of BS 8500-2:2023 over the indicated range of proportions. The compressive strength results are for tests carried out in accordance with BS EN 197-1 with 50% Regen GGBS in combination with the indicated cement. The combination of cement sources in bold text have been evaluated for conformity for less than six months.

In order to establish the designation of the combination as per Table 1 of BS 8500-2:2023, the user requires to know the limestone content of the cement. For cements supplied by Heidelberg Materials UK, this is shown in brackets in the table below. For cements of other sources the user should refer to the supplier for this information.

Composite samples for Heidelberg Materials UK cements and GGBS are obtained by blending not less than 8 spot samples of similar mass, taken at regular intervals throughout the relevant period. For information on composite samples of other cement sources, the user should refer to the supplier.

Cement Source		Compressive Strength N/mm ²		Regen GGBS Percentage Range					
				42.5L		32.5L		22.5	
Company	Source	7 day	28 day	Min	Max	Min	Max	Min	Max
TARMAC	TUNSTEAD	29.1	52.6	14	61	52	73	68	82
HEIDELBERG MATERIALS	PADESWOOD PLC (8-12%)	36.1	54.3	6	65	54	76	71	84
HEIDELBERG MATERIALS	KETTON (3-5%)	33.5	53.4	6	61	52	72	67	81
LAFARGE	CAULDON 52.5N	37.5	55.6	6	60	52	72	66	81
HEIDELBERG MATERIALS	PADESWOOD (3-5%)	33.7	55.2	6	66	53	77	72	84
HEIDELBERG MATERIALS	RIBBLESDALE (3-5%)	33.7	52.0	6	60	50	73	67	81
CEMEX	RUGBY	31.2	50.1	6	61	51	73	68	81
LAFARGE	GLASGOW LAGERDORF	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
TARMAC	DUNBAR	25.0	50.5	31	65	48	80	76	88
SOUTHERN-PREMIER	PLATIN	31.9	52.2	6	60	48	74	69	82
LAFARGE	COOKSTOWN	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
CIMPOR	ALHANDRA 52.5R	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
BREEDON	HOPE	32.4	55.1	6	61	52	73	68	82
CEMEX (LEITH)	ALCANAR	28.1	50.2	19	62	52	75	69	84
TILLCOUNTRY	LAGAN	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
HEIDELBERG MATERIALS	RIBBLESDALE PLC (9-13%)	35.8	50.6	6	61	51	73	68	81
BREEDON	HOPE PLC	33.6	54.3	8	65	55	75	71	83
ELLESMERE	OGGAZ	30.9	54.7	33	69	60	78	74	84

The Regen GGBS contained no additional materials others than those permitted according to BS EN 15167-1.

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.

Signed:

Nina Cardinal

Dr Nina Cardinal, Dipl.Ing., CEng, MICT National Technical Manager