

Conformity Certificate



Regen Ground Granulated Blastfurnace Slag Produced at Sample Period

Port Talbot October 2024

Certificate of Conformity of Regen GGBS

Spot samples of Regen GGBS were taken and tested to determine conformity to the autocontrol requirements of EN 15167-1 "Ground granulated blastfurnace slag for use in concrete, mortar and grout" following the methods given in that standard. The values reported are mean values for the monthly production period.

		Result	EN Limit
Regen GGBS Only			
Fineness m ² /kg		454	min. 275
Magnesia MgO %		8	max. 18
Sulfate SO ³ %		0.33	max. 2.5
Sulfide S ²⁻ %		1.10	max. 2.0
Chloride Content CI %		0.00	max. 0.1
Moisture Content %		0.10	max. 1.0
Aluminia Al ₂ O ₃ %		13	
Note: If the value is \ge 14% the '+SR' restriction will be exceeded if the C ₃ A of	f the CEM I is $> 10^{\circ}$	%.	
Alkalis as Na2O equ. (acid soluble	e)		
Certified Average Alkali (Last 25) %		≤ 1.0	
Mean Alkali content (Last 25) %		0.67	
Declared Mean : Mean last 25 + (SD last 25 x 1.64) %		0.73	
Combination of 50% Laboratory Stock CEM I Portland Cem	ent and 50% Reg	en GGBS	
Initial Setting Time min.		243	> 2 x PC
Activity Index %	7 days	65	min. 45
	28 days	88	min. 70
Laboratory Stock CEM I Portland Ceme	nt Only		
The laboratory stock CEM I Portland cement used in these tests was s	upplied by Heidelb	erg Materia	ls UK.
Initial Setting Time min		148	
Compressive Strength N/mm ²	7 days	45.6	
	28 days	57.9	
The Regen GGBS contained no additional materials other than those perm demonstrate the conformity of the material sold during the month to			

liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence

Signed:

Dr Nina Cardinal, Dipl.Ing., CEng, MICT National Technical Manager

CF

1333-CPR-00134