

Conformity Certificate



Regen Ground Granulated Blastfurnace Slag Produced at Sample Period

Purfleet October 2024

Certificate of Conformity of Regen GGBS

Spot samples of Regen GGBS were taken and tested to determine conformity to the autocontrol requirements of EN 15167-1 "Ground granulated blastfurnace slag for use in concrete, mortar and grout" following the methods given in that standard. The values reported are mean values for the monthly production period.

		Result	EN Limit
Regen GGBS Only			
Fineness m ² /kg		453	min. 275
Magnesia MgO %		7	max. 18
Sulfate SO ³ %		0.30	max. 2.5
Sulfide S ²⁻ %		0.81	max. 2.0
Chloride Content Cl %		0.00	max. 0.1
Moisture Content %		0.12	max. 1.0
Aluminia Al ₂ O ₃ %		13	
Note: If the value is ≥ 14% the '+SR' restriction will be exceeded if the 0	C_3A of the CEM I is > 10°	%.	
Alkalis as Na2O equ. (acid s	oluble)		
Certified Average Alkali (Last 25) %		≤ 1.0	
Mean Alkali content (Last 25) %		0.51	
Declared Mean : Mean last 25 + (SD last 25 x 1.64) %		0.58	
Combination of 50% Laboratory Stock CEM I Portland	d Cement and 50% Reg	en GGBS	
Initial Setting Time min.		249	> 2 x PC
Activity Index %	7 days	65	min. 45
	28 days	89	min. 70
Laboratory Stock CEM I Portland (Cement Only		•
The laboratory stock CEM I Portland cement used in these tests	was supplied by Heidelb	erg Materia	ls UK.
Initial Setting Time min		148	
Compressive Strength N/mm ²	7 days	45.6	
	28 days	57.9	
The Regen GGBS contained no additional materials other than those	,	esults and c	ther tests

demonstrate the conformity of the material sold during the month to the requirements of EN 15167-1.

Tredenority waterials our has used an reasonable care to ensure the information meters contained is accurate our to the extern permitted in raw, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence

Signed:

Dr Nina Cardinal, Dipl.Ing., CEng, MICT National Technical Manager

CF

1333-CPR-00133