Heidelberg Materials UK Second Floor, Arena Court, Crown Lane Maidenhead, Berkshire, SL6 8QZ Padeswood Works 1333-CPR-00255





## **Cement Test Report**

neidelberg ivialerials i ik Ketton

> Stamford PE9 3SX

Tel: 0330 123 2074 Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of Padeswood PLC 52,5N, BS EN 197-1:2011 - CEM II/A-LL 52,5N

Dispatched from Padeswood during week ending 22-Dec-

and during week ending

22-Dec-24 (Week No. 2024-51 )

01-Dec-24 (Week No. 2024-48 ) for 28 day results

Date	Fineness	Setting Time	Soundness	Compressive Strength			Chloride	Alkali	
	Specific Surface (m²/kg)	Initial	Expansion	40mm x 40mm x 160mm Mortar prisms				Certified Average Alkali	Standard
		(mins)	(mm)	2 Days	7 Days	28 Days	%	% Na₂O eq	Deviation
				(N/mm <sup>2</sup> )	(N/mm <sup>2</sup> )	(N/mm <sup>2</sup> )			
Average									
28-Nov-24	490	170	1	30.0	49.0	60.0	0.04	0.50	0.08
Average	490	170	1	30.0	49.0	60.0	0.04		0.08

**Product Declaration:** 

Declared Mean Alkali (%) = 0.75 (Max) Declared Chloride content (%) = 0.07 (Max)

For and on behalf of HEIDELBERG MATERIALS UK

Dr Nina Cardinal, Dipl.Ing., CEng, MICT

National Technical Manager Heidelberg Materials UK Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.