



Heidelberg Materials UK
 Second Floor, Arena Court, Crown Lane
 Maidenhead, Berkshire, SL6 8QZ
 Ribblesdale Works
 1333-CPR-00127



Cement Test Report

Heidelberg Materials UK
 Ketton
 Stamford
 PE9 3SX
 Tel: 0330 123 2074
 Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of
 Ribblesdale PC, BS EN 197-1:2011 - CEM I 52,5N
 Dispatched from Ribblesdale during week ending
 and during week ending

05-Jan-25 (Week No. 2025-1)
 15-Dec-24 (Week No. 2024-50) for 28 day results

Date	Fineness Specific Surface (m ² /kg)	Setting Time Initial (mins)	Soundness Expansion (mm)	Compressive Strength			Chloride %	Alkali	
				40mm x 40mm x 160mm Mortar prisms				Certified Average Alkali % Na ₂ O eq	Standard Deviation
				2 Days (N/mm ²)	7 Days (N/mm ²)	28 Days (N/mm ²)			
06-Jan-25	420	130	1	31.0	44.5		0.07	0.67	0.04
07-Jan-25	410	140		32.0	42.5		0.07	0.68	0.04
08-Jan-25	410	140		31.0	44.0		0.07	0.68	0.04
09-Jan-25	390	150		33.5	44.0		0.07	0.68	0.04
10-Jan-25	395	145		31.5	45.0		0.06	0.67	0.05
Average	405	140		32.0	44.0		0.07		0.05
09-Dec-24	390	135	1	33.5	46.0	58.0	0.07	0.68	0.03
10-Dec-24	405	130		34.0	46.5	60.0	0.07	0.69	0.03
11-Dec-24	395	130		31.0	46.0	58.0	0.07	0.68	0.03
12-Dec-24	400	135		33.0	45.5	57.0	0.07	0.68	0.03
13-Dec-24	400	130		33.0	44.5	57.0	0.07	0.68	0.03
Average	400	130		33.0	45.5	58.0	0.07		0.03

Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Chloride content (%) = 0.07 (Max)

For and on behalf of
 HEIDELBERG MATERIALS UK

Dr Nina Cardinal, Dipl.Ing., CEng, MICT
 National Technical Manager
 Heidelberg Materials UK

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.