

Conformity Certificate



Regen Ground Granulated Blastfurnace Slag Produced at Sample Period

Port Talbot January 2025

Certificate of Conformity of Regen GGBS

Spot samples of Regen GGBS were taken and tested to determine conformity to the autocontrol requirements of EN 15167-1 "Ground granulated blastfurnace slag for use in concrete, mortar and grout" following the methods given in that standard. The values reported are mean values for the monthly production period.

		Result	EN Limit
Regen GGBS Only			
Fineness m ² /kg		490	min. 275
Magnesia MgO %		8	max. 18
Sulfate SO ³ %		0.13	max. 2.5
Sulfide S ²⁻ %		1.13	max. 2.0
Chloride Content CI %		0.00	max. 0.1
Moisture Content %		0.34	max. 1.0
Aluminia Al ₂ O ₃ %		13	
Note: If the value is \geq 14% the '+SR' restriction will be exceeded if the C_{3}	A of the CEM I is > 10°	%.	
Alkalis as Na2O equ. (acid solu	uble)		
Certified Average Alkali (Last 25) %		≤ 1.0	
Mean Alkali content (Last 25) %		0.59	
Declared Mean: Mean last 25 + (SD last 25 x 1.64) %		0.63	
Combination of 50% Laboratory Stock CEM I Portland C	Cement and 50% Reg	en GGBS	
Initial Setting Time min.		274	> 2 x PC
Activity Index %	7 days	65	min. 45
	28 days	83	min. 70
Laboratory Stock CEM I Portland Ce	ement Only		
The laboratory stock CEM I Portland cement used in these tests wa	as supplied by Heidelb	erg Materia	ls UK.
Initial Setting Time min		148	
Compressive Strength N/mm ²	7 days	46.8	
	28 days	59.3	
The Regen GGBS contained no additional materials other than those p demonstrate the conformity of the material sold during the month	n to the requirements o		

liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence

Signed:

Dr Nina Cardinal, Dipl.Ing., CEng, MICT National Technical Manager

UK CA

1333-CPR-00134