

Conformity Certificate



Regen Ground Granulated Blastfurnace Slag Produced at Sample Period

Purfleet January 2025

Certificate of Conformity of Regen GGBS

Spot samples of Regen GGBS were taken and tested to determine conformity to the autocontrol requirements of EN 15167-1 "Ground granulated blastfurnace slag for use in concrete, mortar and grout" following the methods given in that standard. The values reported are mean values for the monthly production period.

		Result	EN Limit
Regen GGBS Only			
Fineness m ² /kg		446	min. 275
Magnesia MgO %		7	max. 18
Sulfate SO ³ %		0.33	max. 2.5
Sulfide S ²⁻ %		0.82	max. 2.0
Chloride Content Cl %		0.00	max. 0.1
Moisture Content %		0.13	max. 1.0
Aluminia Al ₂ O ₃ %		13	
Note: If the value is ≥ 14% the '+SR' restriction will be exceeded if the	C_3A of the CEM I is > 10°	%.	
Alkalis as Na2O equ. (acid s	soluble)		
Certified Average Alkali (Last 25) %		≤ 1.0	
Mean Alkali content (Last 25) %		0.46	
Declared Mean : Mean last 25 + (SD last 25 x 1.64) %		0.54	
Combination of 50% Laboratory Stock CEM I Portlan	d Cement and 50% Reg	en GGBS	
Initial Setting Time min.		243	> 2 x PC
Activity Index %	7 days	69	min. 45
	28 days	91	min. 70
Laboratory Stock CEM I Portland	Cement Only		
The laboratory stock CEM I Portland cement used in these tests	was supplied by Heidelb	erg Materia	ls UK.
Initial Setting Time min		148	
Compressive Strength N/mm ²	7 days	46.9	
	28 days	59.3	
The Regen GGBS contained no additional materials other than thos	se permitted. The above re	esults and c	ther tests

demonstrate the conformity of the material sold during the month to the requirements of EN 15167-1.

The localized materials of the materials of the materials of the materials of the extent permitted in raw, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence

Signed:

Dr Nina Cardinal, Dipl.Ing., CEng, MICT National Technical Manager

UK CA

1333-CPR-00133